

classification report

**Title:**

CLASSIFICATION OF
REACTION TO FIRE
PERFORMANCE
IN ACCORDANCE WITH
EN 13501-1: 2007

Notified Body No:

0833

Product Name:

Premier

Report No:

184696

Issue No:

1

Prepared for:

Newmor, Madoc Works,
Henfaes Lane,
Welshpool,
Montgomeryshire,
SY21 7BE

Date:

3rd July 2009

1. Introduction

This classification report defines the classification assigned to 'Premier', a fabric-backed vinyl wallcovering, in line with the procedures given in EN 13501-1:2007

2. Details of classified product

2.1 General

The product, 'Premier', a fabric-backed vinyl wallcovering, is defined as being suitable for construction applications, excluding flooring and linear pipe thermal insulation.

2.2 Product description

The product, 'Premier', is fully described below and in the test reports provided in support of classification listed in Clause 3.1.

General description		"Type II" fabric-backed vinyl wallcovering
Product reference of wall covering		"Premier Fabric-Backed Wallcovering"
Name of manufacturer		Newmor
Overall wall covering thickness		0.7mm (Stated by sponsor) 0.5mm (Determined by Bodycote warringtonfire)
Overall wall covering weight per unit area		460g/m ² (Stated by sponsor) 454g/m ² (Determined by Bodycote warringtonfire)
Batch reference of wall covering		"100609"
Range reference of wall covering		"Premier"
Colour reference of wall covering		"MX001"
Coating	Product reference	The sponsor has stated that there is no product reference assigned to this component
	Generic type	PVC Plastisol
	Name of manufacturer	Newmor
	Application rate	400g/m ²
	Application method	Lamination
	Curing process	Hot air at a temperature of 220°C for a period of 45 seconds
	Flame retardant details	See Note 1
Fabric Backing	Product reference	"Protex"
	Generic type	Polyester / cotton scrim
	Name of manufacturer	Premier Cotton
	Thickness	0.2mm
	Weight per unit area	60g/m ²
	Flame retardant details	See Note 1
Adhesive	Product reference	"Dixon Turner Heavy"
	Generic type	PVA / starch / water
	Name of manufacturer	See Note 2

	Application rate	200g/m ²
	Application method	Lambswool roller
	Flame retardant details	See Note 1
Primer	Product reference	"Dixon Turner Primer"
	Generic type	PVA / starch / water
	Name of manufacturer	See Note 2
	Application rate	85g/m ² - (wet)
	Application method	Lambswool roller
Substrate	Flame retardant details	See Note 1
	Trade name	"NT D4 604"
	Generic type	Fibre cement board
	Supplier	Scheerders van de Kerkhove (SVK)
	Thickness	6mm
	Density	1800kg/m ³
Brief description of manufacturing process		Vinyl laminating and printing

Note 1: The sponsor of the test has confirmed that no flame retardant additives were utilised in the production of the product / component.

Note 2: The sponsor was unwilling to provide this information.

3. Test reports/extended application reports & test results in support of classification

3.1 Test reports/extended application reports

Name of Laboratory	Name of sponsor	Test reports/extended application report Nos.	Test method / extended application rules & date
Bodycote warringtonfire	Newmor	WF 184495	EN ISO 11925-2
Bodycote warringtonfire	Newmor	WF 184072	EN 13823

3.2 Test results

Test method & test number	Parameter	No. tests	Results	
			Continuous parameter - mean (m)	Compliance parameters
EN ISO 11925-2 (30s exposure - surface)	F _s	6	0	Compliant
	Flaming droplets/ particles		None	Compliant

EN ISO 11925-2 (30s exposure – edge)	F _s	6	0	Compliant
	Flaming droplets/ particles		None	Compliant
EN 13823	FIGRA _{0.2MJ}	3	11.49	Compliant
	FIGRA _{0.4MJ}		10.97	Compliant
	THR _{600s}		1.50	Compliant
	LFS		N	Compliant
	SMOGRA		0	Compliant
	TSP _{600s}		46.92	Compliant

4. Classification and field of application

4.1 Reference of classification

This classification has been carried out in accordance with clause 8 of EN 13501-1:2007

4.2 Classification

The product, 'Premier', a fabric-backed vinyl wallcovering, in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0

The format of the reaction to fire classification for construction products excluding floorings is:

Fire Behaviour		Smoke Production			Flaming Droplets	
B	-	s	1	,	d	0

i.e. B – s1 , d0

Reaction to fire classification: B – s1, d0

4.3 Field of application

This classification is valid for the following end use applications:

- i) Construction applications used over any substrate with a density equal to or greater than 1800Kg/m^3 , having a minimum thickness of 6mm and a fire performance of A2 or better.
- ii) Substrate prepared utilising 'Dixon Turner Primer', a PVA/starch/water based primer, at an application rate of 85g/m^2 .
- iii) Product installed utilising 'Dixon Turner Heavy' a PVA/starch/water based adhesive, at an application rate of 200g/m^2 .

This classification is also valid for the following product parameters:

Product thickness	No variation allowed
Product weight per unit area	No variation allowed
Product composition	No variation allowed
Product colour/pattern	No variation allowed
Product construction	No variation allowed
Product application	No variation allowed

5. Limitations


This document does not represent type approval or certification of the product

SIGNED



.....
Simon Ince
Technical Officer
Technical Department

APPROVED



.....
Janet Murrell
Technical Manager
Technical Department
on behalf of:
Bodycote warringtonfire

This copy has been produced from a .pdf format electronic file that has been provided by Bodycote **warringtonfire** to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without permission of Bodycote **warringtonfire**. The original signed paper version of this report is the sole authentic version. Only original paper versions of this report bear authentic signatures of the responsible Bodycote **warringtonfire** staff.



Bodycote warringtonfire • Head Office • Holmesfield Road • Warrington • Cheshire • WA1 2DS • United Kingdom
Tel: +44 (0) 1925 655 116 • Fax: +44 (0) 1925 655 419 • Email: Info@warringtonfire.net • Website: www.warringtonfire.net

