

TECHNICAL INFORMATION

Physical Properties

Total Weight: 460g/m² (nominal)
 Vinyl Weight: 400g/m² (nominal)
 Substrate Type: Osnaburg Scrim
 Fabric Baker

Substrate weight: 60g/m² (nominal)
 Tensile Strength: MD 80 N/cm (nominal)
 TD 60 N/cm (nominal)
 Tear Strength: 8500 mN (nominal)

Roll Size

137 cm x 27.4m – cut lengths available

Fire Rating:

Class 'O' to the requirements of Approved Document B of the British Building Regulations (Class 1, BS 476 Part 7).
 Euroclass B - s2, d0. Class A ASTM E-84 Tunnel Test.

Adhesive

Fabric backed vinyls – Newmor Heavy.
 Varies with substrate – please enquire.

Bacteria Resistance:

Manufactured to include antimicrobial protection as standard to help in the control of fungi, actinomycetes and bacteria.

Light Fast:

Excellent Light Fastness
 BS EN ISO 105-B02 7/8

LRV = Light reflective value

Specification

Conforms to requirements of BS EN 259 and Federal Specification CCC-W-408A & C and CFFA Quality Standard for Vinyl Coated Fabric Wallcoverings CFFA-W-101A

Stain/Chemical Resistance:

Pass ASTM D-1308-1987 Federal Spot Test.
 Resistant to temporary staining of oils, fats, mild acids and alkalis.

Quality Assurance:

Our management system and production Procedures comply with ISO 9001, the internationally recognized Quality Standard.

Availability:

Every product stocked in depth.
 Please allow 5/7 days for delivery.

Warranty:

Newmor offers a five year warranty against manufacturing defects.
 Full details available on application.

Samples:

Larger samples are readily available on request.

Maintenance:

Fully washable and in most cases products can be scrubbed repeatedly to remove any marks without damaging the product itself.
 Most products are also able to withstand the use of chlorine releasing agent solutions.



British Product | Global Support



Newmor
 WALLCOVERINGS

UK SALES:
 T: 01938 551990
 E: sales@newmor.com

EXPORT SALES:
 T: + 44 (0) 1938 55 2671
 E: enquires@newmor.com